TECHNICAL BULLETIN



**AUGUST 2013** | Rev 9

This issue supersedes all previous issues

# Selection guide for galvanized steel purlin products

### **INTRODUCTION**

This Technical Bulletin provides the appropriate purlin coating class for use in a range of common building applications. It provides guidance and information regarding factors which must be considered to ensure maximum service life of galvanized steel purlin products.

### **PRODUCTS**

The products produced for purlin manufacture are:

- GALVASPAN® G450
- GALVASPAN® G500
- GALVASPAN® G550

Coating classes available are Z350 (standard coating class) and Z450 (optional coating class). Coating class recommendations for a range of building applications are detailed in *Table 1*.

GALVASPAN® steel is manufactured in accordance with Australian Standard AS1397-2011: Continuous hot-dip metallic coated steel sheet and strip – Coatings of zinc and zinc alloyed with aluminium and magnesium. For more information on GALVASPAN® steel refer to the appropriate product data sheet.

## **GENERAL**

As with all metallic coated steel products, the corrosion performance of GALVASPAN® steel is dependant on the interaction of a number of factors. These include the coating class and the environmental factors to which the surface may be exposed.

The extensive range of climatic conditions in Australia (the tropical north, alpine regions in the south-east, heavy surf characteristics of much of the coastline and desert regions of the interior) need to be considered when specifying purlins. In addition to these environmental conditions, building design (particularly exposure of purlins to the external environment) and internal activities within the building must also be considered.

## FACTORS INFLUENCING PURLIN PERFORMANCE

Table 2 "Guide to Atmospheric Exposure Conditions" is provided to assist in establishing the type of exposure conditions that may be encountered in the various environments listed in Table 1. The descriptions covered in this Technical Bulletin are not an exhaustive list and cannot cover all possibilities, therefore any quoted distances from a source are a **GUIDE ONLY**. If further information is required, please contact BlueScope Steel Direct.

BlueScope Steel maintain a central register of product performance in various environmental conditions

and advice should be sought from BlueScope Steel where doubt may exist as to the proper application of the appropriate GALVASPAN® steel coating class. This is particularly so where the proposed structure is used to house activities that are potentially corrosive in nature or generate corrosive emissions. This includes but is not limited to the storage or use of acids and chemicals, fossil-fuel combustion and other process by-products (including heat & moisture). In addition, the concentration and nature of nearby industrial activity in some localities, and the direction, intensity and nature of prevailing winds can also exert an influence.

Table 1: Coating Class recommendations for typical building applications.

BUILDING APPLICATION	ENVIRONMENT DESCRIPTION	COATING CLASS
Enclosed buildings	Non-aggressive, internal environments	Z350
Open sided rural buildings	Non-aggressive, rural environments.  (Refer to "Unwashed Areas" section of this Technical Bulletin).	Z350
Enclosed Industrial Buildings	Non-aggressive environments	Z350 Refer Note (iii)
Carports and awnings	Environment can vary from non- aggressive to aggressive.	Z350 Refer Note (iv) Z450
Other open sided buildings and industrial awnings	Aggressive environments; also those subject to ingress and build-up of airborne corrosive contaminants or high levels of condensation.	Z450 Refer Note (v)
Intensive animal farming, feed lots and similar activities	Extremely aggressive environment.	Z450 Refer Note (v)
Storage of cement, fertilisers, mineral concentrates and other aggressive industrial products	Very aggressive environments.	Z450 Refer Note (v)

### NOTE:

- i The above examples cover a general range of building applications. Due to the variety of factors which can affect service life and product performance where more detailed recommendations or information on specific applications are required, these should be referred back to BlueScope Steel Direct.
- ii This table should be considered in conjunction with *Table 2*.
- iii Consideration must be given to the nature of activities performed within the building. Where potentially corrosive by-products are produced, further consultation with BlueScope Steel Direct is recommended.
- iv Where the environment is considered to be non aggressive, Z350 will give an appropriate service life provided routine maintenance is conducted as recommended by BlueScope Steel. Where the purlin environment is considered to be mildly aggressive, BlueScope Steel recommend that purlins with an increased coating mass (Z450) be used. Should the environment be regarded as extremely aggressive, BlueScope Steel recommend that the purlins be further post painted with an appropriate high build coating system, as recommended by a reputable paint supplier (see <a href="Technical Bulletin TB-2">Technical Bulletin TB-2</a> Overpainting and Restoration of Exterior BlueScope Steel Products).
- v It is important that you consult BlueScope Steel Direct for advice in regard to design of buildings in extremely aggressive environments considering the use of GALVASPAN® G450 Z450, to ensure maximum service life.

There are a number of specific factors which must be considered:

### **Regional Influences**

Current field experience has indicated that certain regions in Australia are more susceptible to problems such as excessive salt and industrial fallout and excessive humidity. These influences can have a detrimental effect on purlin life which must be taken into consideration when designing building structures. Individual areas should be assessed for local field performance prior to final specification. Please contact BlueScope Steel Direct for advice.

## **Unwashed Areas of Buildings**

All surfaces of a building structure where natural rainfall cannot reach are subject to the build up of dust, marine salts, industrial fallout or specific local environment contaminants. In open sided buildings this can include the wind-borne deposits from local industrial or agricultural activities.

Accelerated corrosion can occur when these contaminants combine with night-time condensation resulting in a corrosive electrolyte that over a period of time can contribute to corrosion of galvanized purlins and cladding.

To ensure maximum service life under such conditions these areas should be subject to a regular maintenance programme. Where practical, washing down of the internal surfaces at regular intervals should be conducted. The

frequency of washing is dependant on the local environmental conditions. Washing may be conducted by means of high-pressure water jets, nylon brush cleaning with suitable household detergent solution followed by rinsing and drying.

Where consideration is being given to initial design, which may incorporate unwashed areas and where such cleaning methods may not be appropriate in respect of building function (for example operations, contents etc) please contact BlueScope Steel Direct for advice.

## Accumulation of Condensation or Fallout on Purlins

In applications where there is high levels of condensation or dust within the building it is recommended where possible that purlins be specified with a down turned bottom lip. This will aid with drainage of moisture from the bottom flange and help to reduce accumulation of dust or debris and assist with maintenance to remove buildup inside the bottom flange

## RELATED BLUESCOPE STEEL TECHNICAL BULLETINS

## Technical Bulletin TB-2

Overpainting and Restoration of Exterior BlueScope Steel Products

# REFERENCED AUSTRALIAN STANDARDS

 AS 1397-2011 Continuous hot-dip metallic coated steel sheet and strip – Coatings of zinc and zinc alloyed with aluminium and magnesium

#### NOTE:

All Australian and Australian/New Zealand Standards should be read to incorporate any and all amendments to the most recently published version.

Table 2: Guide to atmospheric exposure conditions

EXPOSURE CONDITION		CORROSIVE INFLUENCE	DISTANCE FROM CORROSIVE INFLUENCE
Aggressive (close distances to surf, industrial pollution and fumes)	Rough, active surf	Salt laden, moist air	500m – 1000m
	Industrial emission	Fallout	300m - 750m
	Fossil fuel combustion	Acid laden air	300m - 750m
Non-aggressive (outer urban, semi-rural areas, well removed from shoreline and industrial pollution)	Rough, active surf	Salt laden, moist air	>1000m
	Calm, still water	Salt laden, moist air	>300m
	Industrial emission	Fallout	>750m
	Fossil fuel combustion	Acid laden air	>750m

### NOTE:

- i Contact BlueScope Steel Direct for exposure classifications which do not meet the above criteria.
- ii For distances less than the minimum shown, please consult BlueScope Steel Direct.

If you have any questions regarding this Bulletin, please contact BlueScope Steel Direct on 1800 800 789.

To ensure you have the most current Technical Bulletin, please go to bluescopesteel.com.au.



The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.



BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin.

GALVASPAN® and BlueScope are registered trade marks of BlueScope Steel Limited.