

COLORBOND® Permagard® steel for coolroom panels

INTRODUCTION

BlueScope Steel's COLORBOND® Permagard® steel has been specifically developed for use in the coolroom industry. COLORBOND® Permagard® steel comprises traditional zinc-coated steel sheet (ZINCFORM® G300S Z275 steel) coated with a custom formulated, factory applied paint system incorporating an antimicrobial additive.

COLORBOND® Permagard® steel is only available in the colour Permagard® White which incorporates Microban® antimicrobial product protection. In Australia Microban® antimicrobial technology is exclusive to coolroom panels made from COLORBOND® Permagard® steel. Microban® protection is a unique antimicrobial technology that inhibits the growth of surface bacteria that may cause odours and stains while actively helping to reduce the risk of cross-contamination.

The specially formulated backing coat on COLORBOND® Permagard® steel has been developed to combine with readily available adhesives to form a strong bond with the foam core of the panel.

This Technical Bulletin outlines the antimicrobial characteristic of COLORBOND® Permagard® steel as well as guidelines for installation and good practice relating to coolrooms.

ANTIMICROBIAL CHARACTERISTIC

Microban® is the global leader in built-in antimicrobial product protection. The Microban® antimicrobial additive is incorporated into the topcoat of COLORBOND® Permagard® steel during the paint manufacturing process to provide antimicrobial properties.

The effectiveness of antimicrobial properties of COLORBOND® Permagard® steel is regularly tested by an independent laboratory in accordance with Japanese Industrial Standard – Harmonised JIS Z2801:2000 “Antimicrobial products – Test for

antimicrobial activity and efficacy”; the method on which International Standard ISO 22196:2011 “Measurement of antibacterial activity on plastics and other non-porous surfaces” is based. Under those test conditions, COLORBOND® Permagard® steel was found to be highly effective against Staphylococcus aureus and Escherichia coli (E-coli) 0157, both of which can be of particular concern in maintaining food hygiene standards.

COLORBOND® Permagard® steel has undergone assessment by HACCP Australia (the recognised independent authority on food-safety programmes) and received endorsement as a FoodSafe product for Ceiling and Wall linings of food storage and processing facilities.

For further detail on antimicrobial performance test work, please visit the following website:

www.colorbond.com/permagard

WARNING: Use of COLORBOND® Permagard® steel is not a substitute for good hygiene practices. Its proper use however, significantly increases the level of protection against bacteria in between cleanings, and regular cleaning should not remove the antimicrobial protection. However, note that any damage to the topcoat surface will result in a reduction in antimicrobial properties. Also be aware that food items should not be stored in intimate contact with COLORBOND® Permagard® steel.

INSTALLATION GUIDE

Coolrooms manufactured from COLORBOND® Permagard® steel have the benefit of ease of installation. However, it is still recommended that you seek professional advice prior to designing and constructing your coolroom.

Listed below are some factors you should consider:

- Consultation of **Corrosion Technical Bulletin CTB-2 Galvanic Protection** and **Corrosion Technical Bulletin CTB-12 Dissimilar Metals** prior to choosing fittings.
- The lightweight nature of a composite panel coupled with an inherent structural capability may make the need for an internal frame for smaller projects obsolete.
- In a coolroom, moisture is ever present. It is **VITAL** to overall corrosion performance that water is allowed to drain freely away from a composite panel. This is especially the case at the base of the panel where poor detailing can allow water to become trapped in the foam core. Once moisture is trapped in a panel, corrosion will be accelerated.
- It is recommended that a dwarf masonry wall be incorporated in the coolroom design. This will allow water to drain away and also protect the base of the coolroom wall.
- Bottom channels of the walling should be manufactured from compatible materials and be designed to allow water to drain freely.

Each panel manufacturer has a different method of joining panels. Most employ a variation of a male/female slip joint. Both corrosion performance and the efficiency of the coolroom will be affected if particular attention is not paid to these joints which must fit snugly together to stop the ingress of moisture. This is especially important if the panels are to be washed down regularly. Mastic type vapour barriers are also recommended for some installations.

For specification details and tools please visit the following website:

www.permagard.steelselect.com

IMPORTANT: It is a condition of a BlueScope Steel warranty* applicable to your project, that your design, construction, installation and ongoing maintenance prevent moisture ingress into panel cores and joints throughout the life of the product. It is also a condition of the warranty* that the recommendations set out in this Technical Bulletin (and any other applicable Technical Bulletins) be complied with.

GOOD PRACTICE

The following good practice is recommended:

- Cleaning chemicals used for cleaning coolrooms should only be used in concentrations and contact durations, as prescribed by the chemical supplier. In any event, the concentration of the active ingredient in the cleaning solution should not exceed 5%.
- Cleaning using soft nylon bristle brooms coupled with water pressures of less than 400psi (2760kPa) is recommended.
- Regular inspection of slip joints, base channels and the general detailing of the coolroom should allow detection of problems before they escalate into major concerns.
- If a problem is observed please contact BlueScope Steel Direct.
- Monitoring of sealant performance at the base of the panel is critical to prevent water ingress.
- Once moisture has entered the panel, it will expand if frozen, causing the panel to bulge. This may cause the seals to be broken and moisture-laden air to enter the panel, potentially causing the panel to bulge further, greatly diminishing the efficiency of the coolroom.
- Bulging of panels could indicate that moisture has entered the panel through the following means:
 - a poorly sealed joint
 - a gap that has developed between the bottom channel and the panel
 - a panel has been punctured (for example by forklift tines)
- Consideration should be given to means of preventing damage to coolroom walling incurred whilst handling stock stored within and around the coolroom.

OTHER COLOURS

For sandwich panel applications requiring colours other than Permagard® White, the product should be ordered as COLORBOND® XIP steel, which does not contain Microban® antimicrobial product protection.

It is generally recommended that lighter colours be utilised for insulated panel applications, rather than darker colours. This is because the higher surface temperatures achieved on dark coloured panels that are externally exposed in service can cause degradation of the insulation core material, and ultimately result in delamination of the steel skin from the core. However, given that the maximum temperature of different colours can vary according to climate, and that the maximum service temperature of the core will depend upon its composition, it may still be possible to develop a suitable sandwich panel system utilising dark coloured skins. It is recommended that you contact BlueScope Steel Direct and a reputable insulated panel supplier, for assistance in determining the suitability of other colours for your proposed application.

RELATED TECHNICAL BULLETINS

Corrosion Technical Bulletin CTB-2
Galvanic Protection

Corrosion Technical Bulletin CTB-12
Dissimilar Metals

If you have any questions regarding this Bulletin, please contact BlueScope Steel Direct on 1800 800 789.

To ensure you have the most current Technical Bulletin, please go to bluescopesteel.com.au.



* Warranty subject to application and eligibility criteria. Warranties are not available for all products and applications. The duration and terms and conditions of any available warranty will depend on product use and application. For full terms and conditions and to determine the eligibility of your project refer to www.bluescopesteel.com.au/warranties or call BlueScope Steel Direct on 1800 800 789.

The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin.



COLORBOND®, Permagard®, ZINCFORM® and BlueScope are registered trade marks of BlueScope Steel Limited.

Microban® is a registered trade mark of Microban Products Company, Huntersville, North Carolina, USA and is used by BlueScope Steel under license. BlueScope Steel holds an exclusive license for the Microban® technology and the Microban® trade mark in Australia and New Zealand for pre-painted steel composite panels.



© 2013 BlueScope Steel Limited ABN 16 000 011 058. BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625. All rights reserved.